

CPI COMP OIL 46

PRODUCT DESCRIPTION

CPI Comp Oil series products are custom-formulated lubricants specifically designed for long life under the severe, demanding conditions normally encountered in recirculating systems such as rotary screw compressors.

CPI Comp Oil series products are based on highly refined “semi-synthetic”, hydro-treated dewaxed paraffinic oil. This special refining coupled with state-of-the-art additive technology results in performance improvements beyond conventional mineral oils and many synthetic oils. Among these are:

- Exceptional oxidative stability
- Long life
- Rust and corrosion inhibited
- Improved economy
- Thermal and hydrolytic stability
- Consistent quality
- Lower equipment maintenance
- Viscosity stability
- Less frictional drag less downtime
- Improved performance
- Resistance to carbon build-up & low sludging tendency
- Low evaporation loss

TYPICAL PROPERTIES*

| | Comp Oil 46 |
|-------------------------------|--------------------|
| Viscosity@40°C ,cSt,ASTM D445 | 48 |
| Viscosity@100°C ,cSt | 7.1 |
| Viscosity@100°F ,cSt | 54 |

Shanghai PingYiao Trading CO., Ltd.

Address: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Website: www.pingyiao.com

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: info@pingyiao.com

| | |
|---|------------|
| Viscosity@210°F ,cSt | 7.3 |
| Viscosity Index ASTM D2270 | 103 |
| Density ,lbs/gal, 60°F | 7.19 |
| Pour Point °F (°C)ASTM D97 | -44(-42) |
| Flash Point,C.O.C., °F (°C)ASTM D92 | 425(218) |
| Fire Point ,C.O.C., °F (°C)ASTM D92 | 450(232) |
| Specific Gravity, ASTM D1298 | 0.865 |
| Water Content | 31ppm |
| Demulsibility, ml oil/ml water/ml emulsion (separation time, min.) | 40-40-0(1) |

*These values are not intended for use in preparing specifications.

Shanghai PingYiao Trading CO., Ltd.

Adress: Xuhui District, Shanghai Caoxi Yinhai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Website: www.pingyiao.com

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: info@pingyiao.com