

SOLEST*-46*

Typical Properties

Viscosity, cSt,

40 °C	50.5
100 °C	7.0
210°F	7.2
100°F	56.2
Viscosity Index	94
Density, lbs/gal	7.70
Pour Point °C(°F).....	-45(-49)
Flash Point °C(°F).....	248(480)
Fire Point °C(°F).....	276(530)
Specific Gravity	0.925
Dielectric Strength (ASTM D-877)	43.6 kv

*The Trademark and Service Mark CPI and the Trademark SOLEST are registered in the United States (CPI[®], SOLESE[®]), and in a number of other countries.

Shanghai PingYiao Trading CO., Ltd.

Address: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Website: www.pingyiao.com

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: info@pingyiao.com